

State of Origin	Sample	Type	Absorption	Bulk SG	Bulk SSD	Apparent SG
NJ	TIL	RCA	5.41	2.31	2.43	2.64
PA	CCF	RCA	5.01	2.33	2.45	2.64
PA	CCN	RCA	5.02	2.33	2.44	2.63
TX	BCB	RCA	5.95	2.28	2.42	2.64
TX	BCL	RCA	5.52	2.29	2.42	2.62
TX	PG	NA	1.83	2.55	2.60	2.68
TX	Sand	NA	1.00	2.62	2.65	2.69

State of Origin	Sample	Type	Absorption (%)	Bulk SG	Bulk SSD	Apparent SG
NY	ALL	RCA	5.33	2.23	2.35	2.53
TX	BCB	RCA	5.95	2.28	2.42	2.64
TX	BCL	RCA	5.52	2.29	2.42	2.62
TX	BCM	RCA	5.13	2.31	2.42	2.61
TX	BCP	RCA	5.42	2.3	2.42	2.62
NJ	BRS	RCA	2.38	2.48	2.53	2.63
PA	CCF	RCA	5.01	2.33	2.45	2.64
PA	CCN	RCA	5.02	2.33	2.44	2.63
TX	MM	RCA	7.24	2.21	2.37	2.63
TX	PRE	RCA	5.61	2.3	2.43	2.64
TX	SCC	RCA	9.68	1.939	2.126	2.386
TX	SMC	RCA	6.23	2.22	2.36	2.58
NJ	TIL	RCA	5.41	2.31	2.43	2.64
TX	G	NA	0.26	2.64	2.64	2.66
TX	PG	NA	1.83	2.55	2.6	2.68
TX	B	NA	10.49	1.478	1.633	1.749
TX	SND	NA	1	2.622	2.648	2.692

DRCA (%)
4.63
5.95
10.33
2.29
2.96
N/A
N/A

DRCA (%)
29.13
2.29
2.96
3.39
3.32
35.07
5.95
10.33
0
1.87
13.7
19.91
4.63
0
0
0
0